



Ultra Acrylic

ULTRA HIGH SPEED FLOOR FINISH

DESIGN FEATURES

- Extra High Gloss, Instant Burnish Response
- Designed for Daily use.
- Reduces Strip Outs
- Formulated for high traffic.
- Scuff and heel mark resistant

PROFESSIONAL RECOMMENDATIONS

- Avoid powdering – apply only when surface temperature is above forty-five degrees.
- Allow extra curing time in hot-humid conditions.
- Do not rush coats – can cause cut-in and dulling.
- Spread evenly for best results – do not overwork finish
- Only apply with clean finish mop. Do not puddle. Thin even coats.
- Dries to high gloss without buffing, but is easily maintained by buffing.

APPLICATION

Applies to floors designed for floor finish that is resilient or non-resilient. Vinyl tile, terrazzo, composite flooring, etc.

SPECIFICATIONS

- Appearance: Opaque liquid
- Odor: Characteristic
- Density (lbs/gal): 8.56
- PH (conc.): 8.8
- Non-volatile: 20% (\pm .5)
- Dry Time: 20-25 minutes
- Slip resistance (ASTM #D2047-82): Exceeds Underwriters
- Stability (40o – 120oF): stable in closed container
- Freeze/thaw stability: Protect from freezing
- Coverage: 1st coat = 1000-1500 sq.ft./gallon
- 2nd coat = 1250-2000 sq.ft./gallon

DIRECTIONS

- Apply finish only to clean, dry floor.
Pour product into clean bucket.
Use clean blended rayon mop.
Dip into finish and press out excess.
No drip mop to floor.
Outline area to be finished, then fill in,
using figure 8 motion, stay 6" off edges.
Make sure coat is dry prior to application.
Apply at least 3-4 coats.
- Wear safety equipment recommended.

Item #102141 =4x1gl; 102105=5gl.pail; 102155 = 55 gl. Drum

Always read MSDS sheets prior to use and wear safety equipment recommended.

PioneerBrite, Inc. • 1381 Heistan Place • Memphis, TN 38104
Phone: 1-800-783-7320 • Fax: 901-725-7697 • Email: info@pioneerbrite.com

www.PioneerBrite.com